

## Safety Grip™

H3401N Black Standard

Date: 11/12/18

### Technical Data Sheet

#### Description

The product is a tough, durable self-adhesive anti slip material for application in a wide range of areas. The material is constructed from a self-adhesive plastic base film. The adhesive is pressure sensitive and is protected by a siliconised treated release paper. The upper surface consists of abrasive aluminium oxide particles held in place by a polymer resin. Prior to setting, the granules are charged by static electricity to help point upwards thus increasing grip levels.

#### Where to normally apply

Designed to provide grip in varied applications even if, once applied correctly, oil, water or other contaminants are present. Perfect for pedestrian traffic or light vehicular traffic.

#### Advantages of using Heskins safety-grip

- Tough, durable.
- High levels of Coefficient of Friction; this is how grip is measured.
- Ease of application.
- Withstands most chemicals that are present in commercial environments.
- Will adhere to most surfaces if the Heskins procedures are followed.

#### Sizes

Heskins produces all sizes and shapes. Maximum width is 1168mm and maximum length is 100m.

#### Packaging

Boxed in a variety of methods dependent on size or customer requirements. The case is marked with a label showing size, quantity, batch number and Heskins internal barcode. Other information is added as required.

#### Application instructions

Please refer to the detailed application instructions.

#### Product durability

When applied typically 3 years.

#### Disposal

This product can be incinerated or disposed of through conventional methods; the waste disposal code is 20.01.04

#### Product Origin

Manufactured in the UK, either converted at the Heskins UK site (Brinscall) or at the Heskins US site (Pennsylvania)

#### Photos



**Safety Grip™**

H3401N Black Standard

Date: 11/12/18

**Heskins H3401N Standard Safety Grip® data sheet**

Subject	Result	Test method
Back carrier	0.1mm PVC	Calliper method
Total applied thickness	0.7mm	Calliper Method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel (g/25.4mm <sup>2</sup> )	1500↑	PSTC-4
Tensile strength (Kg/25.4mm <sup>2</sup> )	6.0↑	PSTC-31
Tear resistance (g)	5600 +/- 200	PSTC-39
Peel adhesion, N/25mm	23.5	180° FINAT FTMI
Tensile strength, N/25mm	68.0	Lloyd, 500N load cell
Elongation at break	25%↑	PSTC-31
Temperature range	-40°C to +70°C	See notes below
Maximum size of production roll	1168mm x 100m	N/A
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

*The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)*

**Safety Grip™**

H3401N Black Standard

Date: 11/12/18

Colour	RAL Reference
Black	9004
Blue	5000
Brown	8002
Green	6010
Yellow	1023
Red	3020
Orange	2004
Fluorescent Yellow	1016
White	9003
Beige	1000
Light Brown	-
Grey	7004
Red/White	3000 & 9016
Black/Yellow	1023 & 9017
Vivid Hazard	1018 & 9011

**LRV Test Results**

Lab. No.	Client's Mark	Av. LRV	Range
072/17	H3401N - Black	3.8	0.16
073/17	H3401G - Brown	6.5	0.49
074/17	H3401F - Fluorescent Yellow	103.6	0.71
075/17	H3401V - Green	7.5	0.29
076/17	H3401S - Grey	30.3	0.48
077/17	H3401O - Orange	30.1	0.82
078/17	H3401R - Red	13.3	1.71
079/17	H3401W - White	83.7	0.29
080/17	H3401Y - Yellow	48.4	0.59
081/17	H3401B - Blue	7.7	0.41

The above tests were conducted in accordance with test standards, the tests were conducted at recognised independent friction testing laboratories, and copy certificates are available on request. Pendulum is a dynamic test, for static tests, we also have results ASTM C 1028-96.

**Safety Grip™**

H3401N Black Standard

Date: 11/12/18

Coefficient of friction data

Test	Dry surface test result	Wet surface test result	Test Standard
Pendulum	102 TRL	71 TRL	BS EN 13036-4
DIN51130	R13		Certificate 97910801.001
DIN51097	Inclination 30°- C		97910801.004
NFSI	High traction		Expiry: 15/7/19

Coefficient of friction data

Safety-Grip®	Dry surface test result	Wet surface test result
Standard	102 TRL	71 TRL

*The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests, we also have results ASTM C 1028-96.*

Temperature Range

Safety-Grip®	Temperature	Observations
Black Standard Anti-slip Tape H3401	-40°C	No visible evidence of peeling or loss of adhesion
Black Standard Anti-slip Tape H3401	+70°C	No visible evidence of peeling or loss of adhesion

All the above data is for reference only.

© Heskings Ltd 1997-2018